

Comparison of Scotch® Box Sealing Tapes

Product	Tape Structure (Backing/Adhesive)	Backing Thickness mils (mm)	Total Thickness mils (mm)	Adhesion to Steel oz./in. (N/100 mm)	Tensile Strength lbs./in. (N/100 mm)	Elonga at Brea
ASTM Test Method:		D-3652	D-3652	D-3330	D-3759	D-3759
371	Polypropylene/Synthetic Rubber	1.2 (.030)	1.9 (.048)	45 (49)	22 (385)	160
372	Polypropylene/Synthetic Rubber	1.4 (.035)	2.2 (.056)	45 (49)	26 (455)	160
373	Polypropylene/Synthetic Rubber	1.6 (.041)	2.5 (.064)	50 (55)	30 (525)	160
375	Polypropylene/Synthetic Rubber	2.0 (.051)	3.1 (.079)	55 (60)	35 (613)	160

Adhesive sticks quickly to a variety of materials, including corrugated fibreboard
 Bonds instantly and resists tearing and splitting for added security
 High performance tape resists nicks, abrasions, moisture and scuffing
 Conformable backing ensures a tight seal around corners and rough areas